



FR50 Carpet Underlay

Technical Data Sheet

Felt is recommended for Axminster and Wilton carpet where the seams bed in to the felt giving an excellent finish. The FR range is widely used in areas of high traffic such as pubs, nightclubs and hotels. It gives an unmatched mix of value and wear for our contract customers.

Fibre composition:	Jute/wool/mixed fibres (100% recycled)
Nominal weight:	1695g/m² (+/- 5%) (50oz/yd²)
Nominal thickness:	11mm (+/- 0.5mm)
Roll width:	Standard 1.37m
Roll length:	12.5m/11.0m
Standard roll area:	17.125m²/15.07m²
Flame retardancy: BS4790:1987 (Hot metal nut test)	Achieves a 'low radius of effects of ignition' - no more than 20mm against maximum permitted of 35mm for low radius classification.
Static loading: BS4939	Thickness loss after 24 hours loading and 24 hours recovery: Retained 56%
Sound Impact: BS2750 Part 8: 1980	Weighted impact sound improvement 24dB
Thermal Resistance: BS4745	2.6 Togs
Other Information:	Our products are tested to the BS5808



Anglo Recycling Technology Ltd

Tong Lane, Whitworth

Rochdale, Lancashire, OL12 8BG

Tel: +44 (0)1706 853513 Fax: +44 (0)1706 853625

Email: info@anglore recycling.com

Web: www.anglore recycling.com

Note: This sheet is for guidance only and is not intended as a product specification